

Nano Ceramic Tint – 25%

Product Details

- Rejects significant amount of infrared heat (IRR), helping to maintain a consistent indoor temperature.
- Blocks 99.9% of UV light.
- Non-metallic/non-conductive: ensures no signal disruption to Wi-Fi, cellular, or radio signals.
- Can help meet compliance with building codes and energy standards.
- Thickness: 2 Mils

Performance Criteria	Nano Ceramic Tint – 25%
Visible Light Transmitted	25%
Infrared Heat Rejection (IRR)	99%
UV Rejection	99.9%
Total Solar Energy Rejected	63%
Glare Reduction	70%

Application Instructions

Clean the glass thoroughly, measure and cut the film to size, then apply it using a slip solution and squeegee to remove bubbles. Ensure proper alignment and trim any excess film. Allow the film to cure for 24–72 hours for full adhesion and clarity. We recommend a Snapguard Solutions 4-piece window film installation kit available on snapguardsolutions.com.

Technical Information

The technical data, recommendations, and statements provided by Snapguard Solutions are based on tests and experiences we believe to be reliable. However, Snapguard Solutions does not guarantee the accuracy or completeness of this information and assumes no liability for its use.

Product Use

Many factors beyond Snapguard Solutions' control—unique to each user's environment and application—can impact product performance. It is the sole responsibility of the user to evaluate the suitability of the product for their intended use and method of application.

Warranty, Limited Remedy, and Disclaimer

Unless otherwise stated in specific product literature or packaging, Snapguard Solutions warrants that its products meet applicable specifications at the time of shipment. SNAPGUARD

SOLUTIONS MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. In the event of a warranty claim, Snapguard Solutions' sole obligation will be to replace the product or refund the original purchase price.

Limitation of Liability

To the extent permitted by law, Snapguard Solutions shall not be liable for any direct, indirect, incidental, or consequential damages arising from the use or inability to use its products, regardless of the legal theory involved, including but not limited to warranty, contract, negligence, or strict liability.

The information provided in this report is believed to be reliable; however, due to the wide range of variables outside of our control, Snapguard Solutions does not guarantee that specific results will be achieved. For complete product specifications and terms of sale, please contact Snapguard Solutions directly.



Snapguard Solutions

2150 Chenault Dr, Dallas, Texas 75006

626-342-6602

www.snapguardsolutions.com

UPDATED JUNE 2025